Slip Check to AS 4586:2013

Husky 450 Anti Slip Tape

NATA Accreditation Number 17139

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

Accredited for compliance with ISO/IEC 17025

NATA is a signatory to the APLAC mutual recognition arrangement for the mutual recognition of the equivalence of testing, calibration and inspection reports

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street, Blacktown NSW 2148 Australia
T (+61) (2) 9621 3706 F (+61) (2) 9621 8891

ABN 80 118 534 768
www.SafeEnvironments.com.au
info@safeenvironments.com.au

SlipCHECK
A division of Safe Environments Pty Ltd
www.SafeEnvironments.com.au

4/40 Bessemer Street
Blacktown NSW 2148
Phone 02 9621 3706
ABN 80 118 534 768

26 February 2016

Test Report No. M0144

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586:2013 Appendix A (Wet Pendulum Test)

The slip resistance Classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface.

Requested by:	Husky Tape
Client Address:	12/56 Norcal Road Nanawading VIC 3131
Product Manufacturer:	Husky Tape
Product Description:	Husky 450 Anti Slip Tape
Test conducted according to:	AS 4586:2013 Appendix A
Location:	Slip Check Pty Ltd Test Facilities, Melbourne VIC 3000
Conducted by:	Nasser Cura

Date:	26 February 2016	Temperature:	22°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	NA		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	85	85	84	84	83

Reported SRV of Sample:	**84**
Class:	**P5**

NATA ACCREDITED FOR TECHNICAL COMPETENCE

Martin Daniel
Materials Scientist

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd